

試驗報告

報告編號: TV-12-02187X

數: 1 OF

報告日期: 101年 08月 27日

商: 保旺塑膠有限公司 託

地 雲林縣大埤鄉豐田工業區豐田路55號 址:

供 料 商: 樣 品 名 稱: PVC發泡板

品 HD-100 產 型 號: 顏 色: 米黄&棕色

保旺塑膠有限公司 收 件 101年 08月 14日 日 期:

101年 08月 14日~101年 08月 27日 試 驗 日 期:

參考CNS 2536(1992) 試 法:

備 以上資料由顧客提供(收件及試驗日期除外)

試驗結果

試驗項目	試驗結果	規範要求
密度(kg/m3)	94. 2	85~110
導熱係數(W/m·K) (平均溫度:20±5℃)	0. 035	0.045以下
抗彎強度(kgf/cm²)	23. 5	2.0以上
抗壓強度(kgf/cm²)	9. 1	1.0以上
吸水量(g/100cm²)	0.005	1.0以下
燃燒性	3秒鍾以內火焰熄滅, 且未超過燃燒界線	3秒鍾以內火焰熄滅, 且未超過燃燒界線

註:1.本試驗報告導熱係數試驗委託SGS材料及工程實驗室-高雄執行

2. 規範要求由委託單位提供

-00 0 -

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明,此報告結果僅對測試之權品負責。本報告未經本公司書面許可,不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms and conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/nTerms-and-Conditions/Terms-e-Document. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized attention, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.