

TEST REPORT

REPORT NO.: HV-10-07721XA

PAGE: 1 OF 3

DATE: NOVEMBER 18, 2010

PROWANG PLASTIC CO., LTD.

NO.55, FENGTIAN RD., DAPI SHIANG,
YUNLIN COUNTY 63147, TAIWAN (R.O.C)

The following merchandise was submitted and identified by the vendor as:

Product Description : PVC PROCELL
Style/Item No. : C-100
Manufacturer/Vendor : PROWANG PLASTIC CO., LTD.
Country of Origin : Taiwan

We have tested the submitted sample(s) as requested and the following results were obtained :

Test Required : (According to client's test specification, please see following sheets in detail.)

Compressive Strength


Test Result :

-PLEASE SEE ATTACHED SHEETS-

Date of Receive : NOVEMBER 05, 2010

Date of Testing : NOVEMBER 05, 2010 ~ NOVEMBER 16, 2010

Signed for and on behalf of
SGS Taiwan Ltd.


Given Chang
Manager

TEST REPORT

REPORT NO.: HV-10-07721XA

PAGE: 2 OF 3

DATE: NOVEMBER 18, 2010

Compressive StrengthTest Equipment :

Name	Brand	Model
Universal Material Testing Machine	INSTRON	5569

Lab Environmental Conditions :

Ambient temperature: 23±2°C

Relative humidity: 50±5%RH

Test Method :

ASTM D1621-00 Standard Test Method for Compressive Properties Of Rigid Cellular Plastics

Test Conditions :

Rate of Compression : 10 mm/min

Average Width : 50.57 mm

Average Width : 50.53 mm

Average Height : 18.42 mm

Test Result :12.4 kgf/cm² (1.22 MPa) (176 psi)

TEST REPORT

REPORT NO.: HV-10-07721XA

PAGE: 3 OF 3

DATE: NOVEMBER 18, 2010

Test Photo :



Test Sample

— The End of Test Report —