

PROWANG® PROLIGHT PVC RIGID FOAM SHEET

Certification of ISO 9001:2008. Made in Taiwan Qualification.

LIST OF CHEMICAL RESISTANT

Name of Chemical	Temperature °C		
	20 °C	40 °C	60 °C
Concentrated Hydrochloric Acid	△	X	X
Concentrated Sulfuric Acid	△	X	X
Sulfuric Acid 30%	◎	◎	△
Concentrated Nirtic Acid	△	X	X
Nitric Acid 40%	◎	◎	△
Formic Acid 100%	△	X	X
Lacitic Acid	◎	△	X
Caustic Soda 40%	◎	◎	◎
Ammonia Water	◎	◎	△
Sodium Disulfide	△	X	X
Acetone	X	X	X
Ethyl Alcohol	◎	◎	△
Butyl Alcohol	◎	◎	△
Toluene	X	X	X
Formalin	◎	◎	△
Carbon Disulfide	X	X	X
Carbon Tetrachloride	△	X	X
Acetic Acid 90%	△	X	X
Butyl Acetate	X	X	X
Gasoline	◎	◎	△
Glycerine	◎	◎	◎
Solution of Spraying Paints	X	X	X
Chlorine (Gas, dired) 100%	X	X	X
Bleaching Solution	◎	◎	X
Sea water, Salt water	◎	◎	◎
Starch (carbohydrate) Solution	◎	◎	◎
Brewing Water	◎	◎	◎

- ◎ Suitable for use (Color and appearance that is no changeable)
 △ Acceptable for use (Appearance is no changeable but for color)
 X Impossible for use (Color and appearance is changeable.)